

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

Rec'd PCT/PTO

04 FEB 2005

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
4 March 2004 (04.03.2004)

PCT

(10) International Publication Number  
WO 2004/018567 A1

(51) International Patent Classification<sup>7</sup>: C09B 67/22,  
D06P 3/54

561-0801 (JP), SETO, Wataru [JP/JP]; 2-7-4-302,  
Sumiyoshi, Ikeda-shi, Osaka 563-0033 (JP).

(21) International Application Number:  
PCT/EP2003/008582

(81) Designated States (*national*): AE, AG, AI, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,  
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,  
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,  
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,  
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE,  
SG, SK, SI, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,  
VC, VN, YU, ZA, ZM, ZW.

(22) International Filing Date: 2 August 2003 (02.08.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
2002-231524 8 August 2002 (08.08.2002) JP

(84) Designated States (*regional*): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,  
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,  
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): DYSTAR  
TEXTILFARBEN GMBH & CO. DEUTSCHLAND  
KG [DE/DE]; Industriepark Höchst, Gebäude B 598,  
65926 Frankfurt am Main (DE).

## Published:


— with international search report

(72) Inventors; and


(75) Inventors/Applicants (*for US only*): HIHARA, Toshio  
[JP/JP]; 2-11-40 Wakaba, YahataNishi-ku, Kitakyusyu-shi,  
Fukuoka 806-0066 (JP). INOUE, Hiroshi [JP/JP];  
2-10-17-102 SoneNishimachi, Toyonaka-shi, Osaka

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: YELLOW DISPERSE DYE MIXTURE WHICH HAS A HIGH LEVEL OF LIGHT FASTNESS



[1]



[2]

(57) Abstract: The present inventions refers to a  
dye mixture comprising from 25 to 80 % by weight  
with respect to the total dyestuff fraction of the  
yellow dyestuff represented by the structural formula  
(1) and from 75 to 20 % by weight with respect  
to the total dyestuff fraction of a yellow dyestuff  
represented by the structural formula (2) wherein R  
denotes a C<sub>1</sub> to C<sub>4</sub> hydroxyalkyl group.

WO 2004/018567 A1

BEST AVAILABLE COPY

## Description

5 Yellow disperse dye mixture which has a high level of light fastness

The present invention concerns disperse dyes, with which polyester-based fibers can be dyed a good yellow color, which have excellent light fastness and with which the dyeing temperature dependence is  
10 low.

Cloth comprising polyester fibers is often used as automobile seat material, but in recent years a demand has arisen as a result of the increasing importance of the fashion aspects of automobile interior  
15 decoration for a wider range of seat colors. However, automobile seats are often exposed to sunlight at high temperatures inside the enclosed cabin and so fading of the seat color is liable to occur and it is difficult to ensure that a good color will be retained over a prolonged period of time. Hence, dyes which have especially good light fastness must be  
20 used for dyeing the polyester fibers used for automobile seats.

However, in the past there were few yellow dyes which had especially good light fastness and a low dyeing temperature dependence, which is to say with which the reproducibility and temperature control at time of  
25 dyeing was achieved easily with a wide range of temperatures being suitable for dyeing, and hardly any yellow dyes which were satisfactory for automobile seat purposes had been found. For example, the dyestuff represented by structural formula [1] below is known from the disclosures of British Patent GB 1105568 and Japanese Examined  
30 Patent Publication Hei4-24470, but although this dyestuff is excellent in terms of its light fastness and can be used generally for dyeing polyester fibers in automobile seat applications, the dyeing temperature dependence is high and temperature control during dyeing is difficult. Furthermore, the dyestuffs which can be represented by the structural


**BEST AVAILABLE COPY**

formula [2] mentioned below are known from the disclosures of DE-A 2212755 and Japanese Patent JP2506594 but, although these dyestuffs have a low dyeing temperature dependence, there is a problem with light fastness when they are used for automobile seat materials.


As a result of a thorough investigation based on an understanding of the situation described above carried out with a view to providing a yellow dye which has good light fastness and a low dyeing temperature dependence, and which is suitable for dyeing the polyester-based fibers which are used in automobile seat applications, the inventors have surprisingly found that the aforementioned objectives can be realized by means of the specified dye mixtures of this invention.

As a result of various investigations carried out with a view to providing a method whereby the dyeing temperature dependence can be reduced while retaining the excellent light fastness of the yellow dyestuff by structural formula [1] indicated below, the inventors have discovered that if a mixture with the dyestuff represented by the structural formula [1] indicated below of a dyestuff which can be represented by structural formula [2] indicated below, or with the further addition of the dyestuff represented by [3], is used, not only is the dyeing temperature dependence reduced when compared with the situation where the dyestuff represented by structural formula [1] indicated below is used alone, but there are cases where the light fastness is also increased, and the invention is based upon this discovery.

That is to say, the invention refers to a dye mixture comprising from 25 to 80 % by weight with respect to the total dyestuff fraction of the yellow dyestuff represented by the structural formula [1]



and from 75 to 20 % by weight with respect to the total dyestuff fraction of a yellow dyestuff represented by the structural formula [2]




5

wherein R denotes a C<sub>1</sub> to C<sub>4</sub> hydroxyalkyl group.

The inventive mixture contains preferably from 50 to 70 % by weight of the yellow dyestuff represented by the structural formula [1] and  
 10 from 50 to 30 % by weight of the yellow dyestuff represented by the structural formula [2].

In those cases where the proportion of the dyestuff of the formula [2] is too small the improving effect on the dyeing temperature dependence  
 15 is small. Furthermore, conversely, in those cases where the amount of the dyestuff of the formula [2] is too great this results in a lowering of the light fastness.

In a preferred embodiment of the present invention the inventive  
 20 mixture contains up to 20 % by weight with respect to the total dyestuff fraction of the yellow dyestuff of the formula [3]



In an especially preferred embodiment of the present invention the inventive mixture contains 5 to 15 % by weight with respect to the total dyestuff fraction of the yellow dyestuff of the formula [3].

- 5 Furthermore, the inventive mixture may contain red dyestuffs and blue dyestuffs in an amount to achieve dyeing of the desired color.


The inventive mixtures can easily be obtained by admixing the dyestuffs of the formulae [1], [2] and [3] in the desired amounts.

10

The dyestuffs of the formulae [1], [2] and [3] are insoluble or sparingly soluble in water and so a dye bath or a printing paste where they have been dispersed as fine particles in an aqueous medium using a condensate of naphthalene sulfonic acid and formaldehyde, a higher alcohol sulfuric acid ester, a higher alkylbenzene sulfonic acid salt or  
15 the like as a dispersing agent is prepared for dyeing polyester fibers using the dye mixture of the present invention and the dyeing can then be carried out by immersion dyeing or printing. For example, in the case of immersion dyeing, dyeing with excellent fastness can be achieved  
20 with polyester-based fibers or mixed weave products if the usual dyeing process methods such as the high temperature dyeing method, the carrier dyeing method, the thermosol dyeing method or such like method is used.



- 25 Examples 1 to 7 and Comparative Examples 1 and 2

The dyestuffs of the formulae [1] and [3] and the dyestuffs of the formulae [2-1], [2-2] and [2-3]



[2-1]

30



were mixed in the proportions disclosed in Table 1 below.

5 The dyestuff mixture (16 mg) and 49 mg of dispersing agent consisting of naphthalene sulfonic acid/formaldehyde condensate, higher alcohol sulfuric acid ester or the like were mixed together and the mixture was dispersed in 100 ml of water which contained dye promotor and acetic acid/sodium acetate pH buffer solution to prepare a dye bath, and 5 g  
10 of polyester cloth was immersed in this dye bath and dyed for 30 minutes at 135°C and then reduction cleaning, rinsing with water and drying were carried out in the usual way and yellow dyed material was obtained.

The light fastness of the dyed material was evaluated in accordance  
15 with the Toyota Automobile Co. light fastness test specifications and the light fastness was good in Examples 1 to 7 according to the present invention. In Examples 1, 5 and 6 where the dyestuffs of the formulae [1] and [2] were mixed in the proportion of 55 % by weight and 45 % by weight, respectively, and in Example 7 where they were  
20 mixed in amounts of 65 % by weight and 35 % by weight, respectively, the light fastness was better than that in the case where the dyestuff of formula [1] had been used alone. Moreover, the light fastness test was carried out using a high energy xenon lamp fadometer from the Suga Test Machine Co. as the testing apparatus  
25 under conditions of radiation intensity 150 W/m<sup>2</sup> (300 - 400 nm), with a light/dark irradiation procedure including 38 cycles with an irradiation time of 3.8 hours and a dark time of 1 hour as 1 cycle at a black panel

temperature of  $73 \pm 3^\circ\text{C}$ . The tests were carried out with the test cloths backed with urethane.

Then the dyeing temperature dependence was evaluated using the method outlined below. The same dyes as used earlier when evaluating light fastness were mixed in the proportions shown in Table 1. The dye mixture (29 mg) and 86 mg of dispersing agent consisting of naphthalene sulfonic acid/formaldehyde condensate, higher alcohol sulfuric acid ester or the like were mixed together and the mixture was dispersed in 100 ml of water which contained dye promotor and acetic acid/sodium acetate pH buffer solution to prepare a dye bath, and 5 g of polyester cloth was immersed in this dye bath and dyed for 30 minutes at  $130^\circ\text{C}$  or for 30 minutes at  $120^\circ\text{C}$  and then reduction cleaning, rinsing with water and drying were carried out in the usual way and dyed materials were obtained. The density of the dyed material obtained at  $120^\circ\text{C}$  was compared with the density of the dyed material obtained at  $130^\circ\text{C}$  and with the dyed materials of Examples 1 to 7 according to the invention, the difference between the densities obtained on dyeing at  $120^\circ\text{C}$  and on dyeing at  $130^\circ\text{C}$  was small, showing that the dyeing temperature dependence was small. On the other hand, in the case of Comparative Example 1 where the dyestuff of formula [1] was used alone there was a marked difference in density and the dyeing temperature dependence was large, which is to say that reproducibility and temperature control when dyeing were difficult, the temperature range which was suitable for dyeing being narrow.

Table 1


	Example 1	Example 2	Example 3	Example 4	Example 5	Example 6	Example 7	Comp. Ex. 1	Comp. Ex. 2
Dyestuff of Formula [1] % by weight	55	80	25	55	55	55	65	100	-
Dyestuff of Formula [2-1] % by weight	45	20	75	30	-	-	35	-	100
Dyestuff of Formula [2-2] % by weight	-	-	-	-	45	-	-	-	-
Dyestuff of Formula [2-3] % by weight	-	-	-	-	-	45	-	-	-
Dyestuff of Formula [3] % by weight	-	-	-	15	-	-	-	-	-
Light Fastness	4 - 5	4	4	4 - 5	4 - 5	4 - 5	4 - 5	4	3 - 4
$\Sigma$ K/S ratio of density of dyed material obtained at 120°C when the density of the dyed material obtained at 130°C was taken to be 100	80	75	75	85	75	75	75	50	65



By means of this invention it is thus possible by mixing a dyestuff of the formula [2], or the dyestuff of the formula [3] in addition to this dyestuff, to the dyestuff of the formula [1] to obtain a yellow disperse dye mixture with which the dyeing temperature dependence is greatly improved while maintaining the good light fastness of the Dyestuff of the formula [1].


## Claims

1. Dye mixture comprising from 25 to 80 % by weight with respect to the total dyestuff fraction of the yellow dyestuff represented by the structural formula [1]



[1]

and from 75 to 20 % by weight with respect to the total dyestuff fraction of a yellow dyestuff represented by the structural formula [2]




[2]

wherein R denotes a C<sub>1</sub> to C<sub>4</sub> hydroxyalkyl group.

2. Dye mixture according to claim 1 which contains from 50 to 70 % by weight of the yellow dyestuff represented by the structural formula [1] and from 50 to 30 % by weight of the yellow dyestuff represented by the structural formula [2].

3. Dye mixture according to claim 1 and/or 2 which contains up to 15 % by weight with respect to the total dyestuff fraction of the yellow dyestuff of the formula [3]



[3]

4. A method for dyeing polyester-based fibers in which a dyestuff mixture of one of claims 1 to 3 is used.

## INTERNATIONAL SEARCH REPORT

International Application No.

PCT/03/08582

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 C09B67/22 D06P3/54

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09B D06P

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, CHEM ABS Data

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DATABASE WPI Section Ch, Week 199510 Derwent Publications Ltd., London, GB; Class A60, AN 1995-070487 XP002258841 -& JP 06 345989 A (MITSUBISHI KASEI HOECHST KK), 20 December 1994 (1994-12-20) formulas abstract	1,3,4
A	WO 02 059215 A (ANDREOLI ANTON ; CLEMENT ANTOINE (CH); LAUK URS (CH); CIBA SC HOLDI) 1 August 2002 (2002-08-01) claim 7	1-4
A	WO 02 057353 A (ORIENT CHEMICAL IND ; DU PONT (US)) 25 July 2002 (2002-07-25) example 4	1,3,4

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*Z\* document member of the same patent family

Date of the actual completion of the international search

22 October 2003

Date of mailing of the international search report

03/11/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.  
Fax: (+31-70) 340-3016

Authorized officer

Ketterer, M

# INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP03/08582

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 6345989	A	20-12-1994	JP 3260492 B2	25-02-2002
WO 02059215	A	01-08-2002	WO 02059215 A1	01-08-2002
WO 02057353	A	25-07-2002	CA 2423779 A1	25-07-2002
			EP 1334147 A2	13-08-2003
			WO 02057353 A2	25-07-2002
			US 2003039837 A1	27-02-2003